

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

D 1

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup>:</b> <b>C21C 5/52, 5/54</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/14287</b> <b>(43) International Publication Date:</b> 16 March 2000 (16.03.00)
<b>(21) International Application Number:</b> PCT/SE99/01290 <b>(22) International Filing Date:</b> 19 July 1999 (19.07.99)  <b>(30) Priority Data:</b> 9802976-2      3 September 1998 (03.09.98)      SE  <b>(71) Applicant (for all designated States except US):</b> UDDEHOLM TECHNOLOGY AKTIEBOLAG [SE/SE]; Uvåvägen 2, S-683 40 Hagfors (SE).  <b>(72) Inventor; and</b> <b>(75) Inventor/Applicant (for US only):</b> GÖRNERUP, Mårten [SE/SE]; Karlavägen 2, S-114 24 Stockholm (SE).  <b>(74) Agents:</b> HYNELL, Magnus et al.; Hynell Patenttjänst AB, Patron Carls väg 2, S-683 40 Hagfors/Uddeholm (SE).		<b>(81) Designated States:</b> AE, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SK (Utility model), SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i> <i>In English translation (filed in Swedish).</i>
<b>(54) Title:</b> METHOD FOR THE PRODUCTION OF A BULK OF MOLTEN METAL, A METALLURGICAL PRODUCT, AND USE OF SUCH A PRODUCT  <b>(57) Abstract</b>  The present invention relates to a method for the production of a bulk of molten steel in an electric arc furnace, comprising the formation of a foaming top slag. During at least one phase of the production process, a doping agent is added to the top slag with the aim of creating improved conditions for the reduction of the oxidized, valuable metal elements which exist in the top slag. The doping agent has a chemical composition containing 0-5 % Si, 2-7 % C, 0-3 % Mn, the remainder essentially only iron and impurities which can normally appear in raw iron produced in the blast furnace process or other reduction process, a melting point < 1350 °C and consists of essentially homogeneous particles with substantially round or oval shape, obtainable through granulation of a melt with above-mentioned composition, comprising the disintegration of a stream of said melt to drops, which are cooled in a water bath to form a granulate.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Larvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

# METHOD FOR THE PRODUCTION OF A BULK OF MOLTEN METAL, A METALLURGICAL PRODUCT, AND USE OF SUCH PRODUCT

## 5 FIELD OF INVENTION

The present invention relates to a method for the production of a bulk of molten metal, preferably molten steel in an electric arc furnace, comprising the formation of a foaming top slag with a temperature of 1400-1800°C and the supply of oxygen in the form of oxygen gas and/or other oxygen carriers, e.g. metallic oxides, to the molten metal in order to oxidize at least part of the existing silicon in the melt for heat generation and to oxidize at least part of the carbon in the melt for heat generation and to generate gas in the form of CO and/or CO<sub>2</sub> which contributes to the slag foaming, by which the supply of oxygen to the melt also brings about oxidation of metal elements other than silicon in the melt, in this text generally referred to as valuable metal elements, which go into the slag and are reduced there by the addition of reduction agents to the top slag so that these elements to a considerable degree are recovered to the melt.

The invention relates as well to a metallurgical product useable as a doping agent in the production of molten metal, preferably molten steel, in an electric arc furnace to create favourable conditions for the reduction of oxidized, valuable metal elements which have accumulated in the top furnace slag, where the metallurgical product itself participates in the reduction process, contributing to and/or maintain foaming of the top slag as well as giving a surplus of metal to the melt. The invention relates as well to the use of such a metallic product.

## 25 BACKGROUND OF THE INVENTION

Most electric arc furnaces are distinct melting machines, and there is an ongoing search for new means in achieving higher power supply to decrease tap-to-tap times. The thermal loading on the furnace walls and roof during the refining period however limit the maximal effect which can be applied during this stage. By using a foaming slag the radiation from the electric arcs can be shielded, which brings about decreased thermal loading on the surroundings. Further favourable effects are more stable electric arcs and improved heat transfer to the melt. Foamy slag practice according to known techniques comprises the injection of oxygen as well as carbon and/or carbon carriers. Oxygen is injected into the steel to form oxides, which are transferred to the slag, where they are to be reduced by the carbon injected into the slag. CO/CO<sub>2</sub> (g) is formed in the slag during the reduction phase, and the gas-slag emulsion forms a foam.

The foaming of slag in general and in electric arc furnaces in particular has been studied theoretically as well as in practical application and has been a well-established technique for many years in modern electric arc furnace steelmaking. The following references may be mentioned here:

5

Cooper, C.F. and Kitchener, J.A.; *The foaming of molten silicates*, J. Iron and Steel Inst., Vol. 193, pg. 48-55, 1959.

10

Hara, S., Ikuta, M., Kitamura, M. and Ogino, M.; *Foaming of molten slags containing iron oxide*, Tetsu-to-Hagane, Vol. 69, pg. 1152-1159, 1983.

Ito, K. and Fruehan, R.J.; *Slag foaming in electric furnace steelmaking*, Trans. of the ISS (I&SM), Aug., pg. 55-60, 1989.

15

Jiang, R. and Fruehan, R.J.; *Slag foaming in bath smelting*, Met. Trans. B, Vol. 22B, pg. 481-489, 1991.

Zamalloa, M., Warczok, A. and Utigård, T.; *Slag foaming during gas injection*, *Electric Arc Furnace Proc.*, Vol. 49, Toronto, Canada, pg. 197-204, 1991.

20

Masucci, P.; *Process for using foamed slag in stainless steel production*, US Patent No.: 5,395,420, 1995.

25

Even though the foaming of slag has become a well-established technique and is used on a large scale in the production of steel in the electric arc furnace, it is, at least considering the production of high-alloy steels such as stainless steels, still associated with a number of problems which have not yet been solved in a satisfactory manner. One problem has to do with the actual formation and maintenance of an active amount of foam, which requires the supply of large amounts of carbon, of which large parts will not participate at all in either the foaming or reduction processes, but rather disappear with slag and off-gases. Another problem relates to the reduction reactions in the foaming slag, which are generally slow, as nucleation sites are scarce. Molten metal does certainly splash up into the slag to a certain degree, but this is insufficient for the generation of nucleation sites to the extent necessary for achieving the desired reduction rate. To avoid unacceptably long tap-to-tap times, therefore, it is usual that the melt is tapped before valuable metals have been reduced back to the desired degree, which implies loss of valuable metals and problems with the handling of remaining slag. To

35

speed up the reduction process, it has therefore been proposed to dope the slag with fine-grained iron carriers such as filter dust or other metallurgical dust, ore concentrate, iron carbide, mill scale, dried metallurgical sludge, iron powder and low-phosphorus pig iron chips or NiO, as described in the following references:

5 Fudala, B; *Process for recycling the filter dust in an electric arc furnace for producing steel*, US Patent No.: 5,493,580, 1996.

Frits et al; *Process for producing an iron melt*, US Patent No.: 5,611,838, 1997.

10 Görnerup, M; *Studies of Slag Metallurgy in Stainless Steelmaking*, Doctoral Thesis, Div. of Process Metallurgy, Dept. of Metallurgy, KTH, S-100 44 Stockholm, Sweden, 1997.

It has been reported in the above references that the rate of reduction in the slag is increased considerably by the addition of the above-mentioned types of material. Still certain problems remain. One of these has to do with the physical characteristics of the added reduction- and/or doping agents, which can cause a large part of them to disappear before reacting with the oxides in the slag. This implies a cost for lost material, but even more problematic is that a good reproducibility of results in the process becomes difficult to achieve. The addition of elementary carbon in the form of powder is still a problem as a large part of the material is lost on addition, decreasing the reproducibility of the process. Pig iron in the form of chips, which has also been proposed, and which can be formed as a residual product from splashing, burrs etc. and in the working of pig iron, is usually contaminated and is for this reason unsuitable as a doping agent. Furthermore, it is from a physical point of view unsuitable to use e.g. mill scale and similar product forms where the particles have large area/volume ratios.

#### DESCRIPTION OF THE INVENTION

The object of the present invention is to attack the above complex of problems to improve the method for producing a melt in an electric arc furnace which is described in the introduction of this patent application. Characteristic for the invention is that during at least one phase of the production process, a doping agent in the form of a particle-formed, granulated product is added to the top slag with the aim of improving conditions for the reduction of the oxidized, valuable metal elements existing in the slag, as well as participating in the reduction process, contributing to and/or maintaining the slag foaming as well as providing an addition of metal to the melt, where said doping agent fulfills the following requirements, namely:

a) that it has a chemical composition containing 0-5% Si, 2-7% C, 0-3% Mn, the remainder essentially only iron and impurities which can normally exist in pig iron made in the blast furnace process or other reduction process.

5

b) that it has a melting point  $< 1350^{\circ}\text{C}$ , and

10

c) that it consists of essentially homogeneous particles with substantially round or oval form, obtainable through granulation of a melt with the above-mentioned composition, comprising disintegration of a stream of said melt to drops, which are cooled in a water bath to form a granulate.

15

20

25

For the production of the granulate, a specific method can be used, the general principles of which are described in the US-patent 3,888,956. By this known method, raw iron granulate can be produced, in which at least 90 weight-% of the granulate consists of particles with shapes varying from substantially round or oval slices to drops and spheres with sizes varying from 1 mm up to 25 mm measured in the largest dimension of the granules. The granulate can be used in this form as the above-mentioned doping agent according to the invention. The largest particles will however sink quite rapidly through the slag and join the melt, before they have had a chance to participate in the reduction processes to a significant degree. This can be tolerated in many cases, as the granulate also contains a large portion of particles which have a shape and size suitable for use as doping agent according to the invention. As these larger particles reach the melt before reacting with the slag to a significant degree, they will be incorporated into the melt and make themselves useful there through their iron content and because carbon and silicon react with supplied oxygen to exothermically form carbon oxide and/or carbon dioxide, and silicon dioxide respectively.

30

35

There are however disadvantages connected with the doping agent being used as a granulate which, besides particles with a size desirable as doping agent, even contain granules with larger sizes than that which is desired in a granulate with the role of doping agent. These larger particles can seem to hinder the formation of foam, cool the foaming slag as well as diluting the melt with iron, which is undesirable in certain cases, as in e.g. the production of highly alloyed stainless steels. It can therefore be suitable at least in certain cases to use a granulated product of said slag as doping agent, of which at least 80 weight-% consists of particles with a particle size varying between 0.5 and 8 mm measured in the largest dimension of the particles. The rounder the particles, the

more favourable they are with respect to their ability to penetrate the slag and to keep themselves floating in the slag with the aid of gas formation, where the gas is attached to the particles for a considerable length of time. The granulate resides in the slag for a sufficiently long time so that it not only melts, which it does relatively quickly, but also so that the content of carbon and silicon in the granulate manage to react with the oxides of the valuable metal elements in the slag, and to gradually agglomerate to larger agglomerates of molten metal, which sink down through the slag to join the melt. In contrast, irregularly shaped flakes, mill scale, fine powder etc. have very poor penetration ability.

There are several different ways of achieving an agglomerate consisting of homogeneous particles with said shape and said chemistry, where at least 80 weight-% consist of particles with a particle size varying between 0.5 and 8 mm, considered in the largest dimension of the particles, preferably with a size varying between 1 and 5.5 mm.

For example the size and shape of the granulate produced by the method described in said US patent 3,888,956 is regulated by variation of the height of fall of the molten stream before it disintegrates to drops and/or by the height of fall of the drops before they meet the water surface in the cooling bath. As a complement and/or alternative, the obtained granulate can be screened, so that the desired size fraction is obtained.

The addition of doping agent can be made through a lance with a gas carrier, where the lance can be placed through the slag door, furnace wall or furnace roof, or by mechanical feeding from a position above the slag, in the furnace wall or furnace roof. The added doping particles melt quickly in the hot slag and form small drops with large boundary layer area between liquid metal phase and slag, which kinetically favours reduction of metallic oxides. The doping agent contains active contents of dissolved carbon and silicon, which participate as melted drops in the reduction reactions. Dissolved carbon forms CO/CO<sub>2</sub>-gas, which in turn generates and/or maintains the foaming slag and helps to keep the small metal drops suspended in the slag. The achieved reduction and foaming implies a number of advantages in the process, which in certain cases can be vital for obtaining an economically acceptable furnace operation. Thus, the carbon dissolved in the doping agent has several functions: it contributes to and/or maintains formation of the foaming slag, it contributes to keeping the small molten metal drops suspended in the slag, which maintains the foaming, and it participates in the reduction processes.

Also the silicon which is dissolved in the doping agent has several functions. Silicon contributes to the reduction of oxidized valuable metal elements, which most probably decreases the boundary layer tension between slag and doping agent, which further accelerates the reduction reaction. Furthermore, heat is formed through the oxidation of dissolved carbon and silicon. Oxidation of dissolved silicon contributes as well to the formation of slag in the furnace. Finally, the doping agent contributes to a significant addition of iron to the melt when most of the reduction agents--C and Si--in the doping agent have reacted with the slag and a number of smaller drops have agglomerated to larger drops which then sink down through the slag layer into the metal bath.

The raw material of the granulate, which forms the doping agent according to the invention, or from which the doping agent can be obtained by screening or other methods, can be made from a molten raw iron from a blast furnace process or other reduction process, possibly after certain refining, e.g. sulphur removal. However the contents of carbon and silicon, which comprise the essential elements in the doping agent according to the invention, vary most considerably from blast furnace to blast furnace. In order for the doping agent to be useful as a commercial product of high value, with which the electric arc furnace top slag can be doped to produce the desired result from heat to heat, it is desirable that the contents of carbon and silicon in the doping agent be kept within relatively narrow limits within the stated outer limits. Thus the contents of carbon and silicon should not vary more than  $\pm 0.5\%$ , preferably not more than  $\pm 0.3\%$  from the assigned target value within said outer limits. Thus the carbon content in the doping agent should go up to  $(C_x \pm 0.5)\%$ , where  $C_x$  is a number between 3 and 4.5. Preferably the carbon content should be  $(C_x \pm 0.3)\%$ . In a corresponding way the silicon content should be  $(Si_x \pm 0.5)\%$ , preferably  $(Si_x \pm 0.3)\%$ , where  $Si_x$  is a number between 1 and 2.5. The desired contents of carbon and silicon can be obtained through alloying the raw iron with carbon and silicon after possible desulphurization or other treatment of the raw iron.

The amount of added doping agent can be varied within wide limits depending on the composition of the melt, the composition of the doping agent and other factors. Normally the amount of doping agent added to the slag according to the invention can go up to between 5 and 80 kg of doping agent per ton produced steel, which is added to the slag by injection into the slag or in another manner to maintain slag foaming and reduction. Simultaneously, oxygen is added in a balanced amount to the steel to oxidize mainly Si and C in the steel to obtain heat and gas for the slag foaming. Also other metal elements in the steel, e.g. Fe and Cr, are oxidized to a certain degree



and then reduced again when they reach the slag. Other reduction agents may also be added, besides the doping agent according to the invention, e.g. C or Si, to the slag in order to ensure the reduction together with the doping agent according to the invention.

5 The invention is applicable in all metallurgical melting processes where reduction of metallic oxides with a melting point above the process temperature is to occur, including in the production of unalloyed steels, but is especially suitable for the production of steel which contains more than 2% Cr, in particular stainless steels which contain at least 17% Cr, as the invention solves the problems which are particularly  
10 related to the reduction and recovery of chromium from the top slag in electric arc furnaces.

15

20

25

30

35

## CLAIMS

1. Method for the production of a bulk of molten metal, preferably molten steel, in an electric arc furnace, comprising the formation of a foaming top slag with a temperature of 1400-1800°C and the supply of oxygen in the form of oxygen gas and/or other oxygen carriers, e.g. metallic oxides, to the melt to oxidize at least part of the silicon existing in the melt for heat generation and to oxidize at least part of the carbon existing in the melt for heat generation and to generate gas in the form of CO and/or CO<sub>2</sub> as a contribution to the slag foaming, by which the supply of oxygen to the melt also brings about oxidation of other metal elements than silicon in the melt, herein referred to as valuable metal elements, which enter the slag and are there reduced by the addition of reduction agents to the top slag in order that they to a considerable degree are recovered to the melt, characterized in that during at least one phase of the production process, a doping agent in the form of a particle-formed, granulated product is added to the top slag with the aim of creating improved conditions for the reduction of the oxidized, valuable metal elements in the top slag, participating in the reduction process itself, contributing to and/or maintaining the slag foaming as well as adding metal to the melt, said doping agents fulfilling the following requirements, namely:

a) that it has a chemical composition containing 0-5% Si, 2-7% C, 0-3%Mn, the remainder essentially only iron and impurities which can normally exist in pig iron produced in the blast furnace process or other reduction process,

b) that it has a melting point < 1350°C, and

c) that it consists of essentially homogeneous particles with substantially round or oval shape obtainable by granulation of a melt with above-mentioned composition, comprising disintegration of a stream of said melt to drops, which are cooled in a water bath to form a granulate.

2. Method according to claim 1, characterized in that the doping agent has a chemical composition containing 0.2-3 % Si, 2-5 % C, 0.1-3 % Mn, the remainder essentially only iron and impurities which can normally exist in raw iron produced in the blast furnace process or other reduction process.

3. Method according to claim 1 or 2, characterized in that at least 80 weight-% of said particles consist of particles with a particle size varying between 0.5 and 8 mm, measured in the largest dimension of the particles.
- 5 4. Method according to any of the previous claims, characterized in that the particles have a bulk density of 3.0-5.5 kg/l, preferably 3.5-5 kg/l.
5. Method according to claim 3, characterized in that at least 80 weight-% of the particles have a size between 1 and 5.5 mm measured in the largest dimension of the  
10 particles.
6. Method according to claim 1, characterized in that the doping agent has a carbon content of 2.5-4.5%.
- 15 7. Method according to claim 1, characterized in that the doping agent has a silicon content of 1-3%.
8. Method according to claim 1, characterized in that the melt constitutes a steel melt containing at least 2 % Cr.  
20
9. Method according to claim 8, characterized in that the melt constitutes a melt of stainless steel, containing at least 13%, preferably at least 17% Cr.
10. Metallurgical product applicable as doping agent in the production of melts,  
25 preferably steel melts, in electric arc furnaces to create favourable conditions for the reduction of oxidized, valuable metal elements which have accumulated in a furnace top slag, to participate in the reduction processes themselves, to contribute and/or maintain foaming of the top slag and to give an addition of metal to the melt, characterized in that:
- 30 a) it has a chemical composition containing 1-5% Si, 2-7% C, 0-3% Mn, the remainder essentially only iron and impurities which can normally occur in raw iron produced in the blast furnace process or other reduction process,
- 35 b) it has a melting point < 1350°C, and

- c) it consists of essentially homogeneous particles with substantially round or oval shape, obtainable through granulation of a melt with above-mentioned composition, comprising disintegration of a stream of said melt to drops, which are cooled in a water bath to form a granulate.

5

11. Metallurgical product according to claim 10, characterized in that it has a chemical composition containing 0.2-3% Si, 2-5% C, 0.1-3% Mn, the remainder essentially only iron and impurities which can normally appear in raw iron produced in the blast furnace process or other reduction process.

10

12. Metallurgical product according to claim 10, characterized in that at least 80 weight-% of said particles consist of particles with a particle size varying between 0.5 and 8 mm, measured in the largest dimension of the particles.

15

13. Metallurgical product according to claim 11, characterized in that at least 80 weight-% of the particles have a size between 1 and 5.5 mm measured in the largest dimension of the particles.

20

14. Metallurgical product according to one of the claims 10-13, characterized in that it has a carbon content of 2.5-4.5%.

15. Metallurgical product according to one of the claims 10-14, characterized in that it has a silicon content of 1-3 %.

25

16. Use of a metallurgical product with the following characteristics, namely

a) that it has a chemical composition containing 0-5% Si, 2-7% C, 0-3%Mn, the remainder essentially only iron and impurities which can normally appear in raw iron produced in the blast furnace process or other reduction process,

30

b) that it has a melting point < 1350EC, and

c) that it consists of essentially homogeneous particles with substantially round or oval shape, obtainable through granulation of a melt with above-mentioned composition, comprising disintegration of a stream of said melt to drops, which are cooled in a water bath to form a granulate,

35

as a doping agent in the production of an electric arc furnace melt to participate in foaming of the furnace top slag by being added to said top slag, to participate in the reduction of oxidized valuable metal elements which are accumulated in oxide form in the top slag and to recover these valuable metal elements to the melt, and to contribute  
5 itself as an addition of metal to the melt.

17. Use according to claim 16, by which the metallurgical product has a chemical composition containing 0.2-3% Si, 2-5% C, 0.1-3% Mn, the remainder essentially only iron and impurities which can normally appear in raw iron produced in the blast furnace  
10 process or other reduction process.

15

20

25

30

35

## INTERNATIONAL SEARCH REPORT

International application No.

PCT/SE 99/01290

## A. CLASSIFICATION OF SUBJECT MATTER

IPC6: C21C 5/52, C21C 5/54

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC6: C21C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

SE,DK,FI,NO classes as above

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

WPI, EPODOC, JAPIO

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 5395420 A (PASQUALE MASUCCI), 7 March 1995. (07.03.95), claim 1 --	1-17
A	US 5611838 A (ERNST FRITZ ET AL), 18 March 1997 (18.03.97), abstract --	1-17
A	EP 0829545 A1 (USINOR SACILOR SOCIETE ANONYME), 18 March 1998 (18.03.98), abstract --	1-17
A	WO 9858091 A1 (VOEST-ALPINE INDUSTRIEANLAGENBAU GMBH), 23 December 1998 (23.12.98), abstract -- -----	1-17

☐ Further documents are listed in the continuation of Box C.☒ See patent family annex.

## \* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&" document member of the same patent family

Date of the actual completion of the international search

8 November 1999

Date of mailing of the international search report

06-12-1999

Name and mailing address of the ISA/  
Swedish Patent Office  
Box 5055, S-102 42 STOCKHOLM  
Facsimile No. +46 8 666 02 86

Authorized officer

Anna-Maj Magnusson/MP  
Telephone No. +46 8 782 25 00

**INTERNATIONAL SEARCH REPORT**  
Information on patent family members

28/09/99

International application No.  
PCT/SE 99/01290

Patent document cited in search report:	Publication date	Patent family member(s)	Publication date
US 5395420 A	07/03/95	EP 0655508 A,B AT 169964 T DE 69320482 D	31/05/95 15/09/98 00/00/00
US 5611838 A	18/03/97	AT 249593 A AT 400245 B CA 2137766 A EP 0657549 A	15/03/95 27/11/95 11/06/95 14/06/95
EP 0829545 A1	18/03/98	AU 3424797 A BR 9704689 A CA 2210505 A CN 1180751 A FR 2753205 A,B JP 10088223 A	19/03/98 29/12/98 12/03/98 06/05/98 13/03/98 07/04/98
WO 9858091 A1	23/12/98	AT 105997 A AT 405054 B	15/09/98 25/05/99

**This Page Blank (uspto)**